

## MX 9000 2K ACRYLIC



### CHARACTERISTIC PROPERTIES:

MX 9000 2k acrylic made from high quality material and finest types of acrylic resins and the best types of solvents and additives to give high performance, high gloss, fast drying, high resistance to conditions and weather conditions, high resistance to chemicals and solvents.

### PRODUCTS FOR APPLICATION:

- MX 9000 2k acrylic.
- 2k hardener H51.
- 2k thinner T60.

### SUITABLE SUBSTRATES:

- Polyester Putty.
- 2k Filler
- MX 9000 2k acrylic

### MIXING RATIO BY VOLUME %:

100	parts by volume of Acrylic paint.
50	parts by volume of 2K-Hardener H51.

**SPRAY VISCOSITY:** 16-18 second ford cup no. 4.

**DILUTION:** Add 30% acrylic thinner T60.

### PROCESS:

- Apply 2 full coats recommended dry film thickness is 50-60 microns.
- Flash off time 5-10 minutes between coats, 20 minutes before baking.

### PHYSICAL PROPERTIES:

- Density: 1-1.30 gm/cm<sup>3</sup>.
- Viscosity: 250-300 sec 25 °c.

### DRYING TIME:

Drying time	25 °C.	60 °C.
Touch dry	3 hrs.	20 min.
Complete dry	12 hrs.	30 min.

### PACKAGING:

1Liter and 3.7 Litter.

### COLOR:

According to El-Mohandes color chart.

### SHELF LIFE:

5 years at 25 °C.

### MATERIAL SAFETY DATA:

When using these products it is required to comply with the national regulations for health and safety.

