

MX 9000 BASE COAT



CHARACTERISTIC PROPERTIES:

MX 9000 basecoat made from high quality material and finest types of acrylic resins and the best types of solvents and additives to give high performance.

PRODUCTS FOR APPLICATION:

- MX 9000 basecoat.
- Metallic thinner T61.

SUITABLE SUBSTRATES:

- Polyester Putty.
- 2k Filler.
- Basecoat.

MIXING RATIO BY VOLUME %:

100	parts by volume of Base Coat.
100	parts by volume of Metallic Thinner T61.

SPRAY VISCOSITY: 16-18 second ford cup no. 4.

PROCESS:

- Apply 2 full coats recommended dry film thickness is 15-20 microns.
- Flash off time 5-10 minutes between coats.

PHYSICAL PROPERTIES:

- Density: 1 ± 0.02 gm/cm³.
- Viscosity :150-200 sec 25 °c.

DRYING TIME: At 25°C

Touch dry	3-4 min.
Complete dry	15-20 min.

PACKAGING:

1Liter and 3.7 Litter.

COLOR:

According to El-Mohandes color chart.

SHELF LIFE:

5 years at 25 °C.

MATERIAL SAFETY DATA:

When using these products it is required to comply with the national regulations for health and safety.

